

# FLEX-REZ 1084AS

## Alcohol Soluble Polyamide Resin

#### **IMPORTANT CHARACTERISTICS:**

**Flex-rez 1084 AS** is exceptionally high in melt point(185 °C) and should be evaluated in applications demanding high heat resistance. Additionally, **Flex-rez 1084 AS** in solution will not gel at low temperatures, and when added to ordinary polyamide inks, it will impart some gel resistance. Although **Flex-rez 1084 AS** is not a film former as other polyamide resins, it lends hardness to the film that makes it useful as a modifier for improving grease, scratch and rub resistance. **Flex-rez 1084 AS** offers great potential in the formulation of unique, high performance inks for a variety of synthetic polymer substrates.

#### **APPLICATIONS:**

- Gravure inks
- Coatings and overprint varnishes
- Flexographic inks
- Not a film former

### **BENEFITS:**

- High heat resistance
- Fast solvent release
- Grease resistance
- Modifier for film formers
- Gel resistance

#### **Typical Properties**

Property	Value	Unit	Test Method
Acid value	Max.15	mgKOH/g	
Amine value	Max.15	mgKOH/g	
Viscosity (45% N.V. in 95% Ethanol)	Е		G-H, End-End, 25 °C
Colour	Max.18		
Melting point	185	°C	Ring & Ball method

Updated 5/18/11 TM

## ® and ™ Licensed trademarks of Lawter, Inc.

#### **DISCLAIMER**

The information provided herein was believed by Lawter, Inc. ("Lawter") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product, and to determine the suitability of the product for its intended use. All products supplied by Lawter are subject to Lawter's terms and conditions of sale. LAWTER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY LAWTER, except that the product shall conform to Lawter's specifications. Nothing contained herein constitutes an offer for the sale of any product.